

PROPERTIES		TEST METHOD	VALUES
<b>Filament blend</b>			PET/PA
<b>Web bonding</b>		EN 29092	hydrolace
<b>Mass per unit area</b>	g/m <sup>2</sup>	EN 9073-1	target 200
<b>Thickness</b>	mm	ISO 9073-2	target 0,75
<b>Tensile strength Machine direction</b>	N	EN 13934-1	target 620
<b>Tensile strength Cross direction</b>	N	EN 13934-1	target 700
<b>Tear strength Machine direction</b>	N	EN 13 937	target 40
<b>Tear strength Cross direction</b>	N	EN 13 937	target 40
<b>Elongation at break Machine direction</b>	%	EN 13934-1	target 55
<b>Elongation at break Cross direction</b>	%	EN 13934-1	target 60
<b>Surface resistivity</b>	Ohms	EN 100 015/1	target 10 <sup>9</sup>

Technical data on this data sheet refer to non-binding reference samples only. Binding specifications will be agreed separately. The customer is responsible for conducting his/her own tests to determine for him/herself the suitability of the products for his/her particular purposes. The customer is especially responsible for testing the suitability of the product for specific post-treatments before large-scale production.

PACK SYSTEM  
[www.tytpacksystem.com](http://www.tytpacksystem.com)