


EVO 240 SG 110SP AS

Reinforced with Spunbond non-woven



Data Sheet



EVOLON	Filament blend	(DIN 60000-T01)	PES / PA 6
	Color of the surface web		GREY
	Evolon (both layers) weight	(EN 964-1)	130 g/m ²

REINFORCEMENT	Web composition	(DIN 60000-T01)	PES
	Web weight	(EN 964-1)	110 g/m ²

COMPOSITE	Web bonding	(EN 29092)	hydrolace
	Mass per unit area	(EN 964-1)	240 g/m ²
	Standard width		1600 mm
	Thickness	(EN 13934-1)	1,00 mm
	Tensile strength (md)	(EN 13934-1)	800 N
	Tensile strength (cd)	(EN 13934-1)	600 N
	Elongation at break (md)	(EN 13934-1)	50%
	Elongation at break (cd)	(EN 13934-1)	50%
	Tear resistance (md)	(EN 13937)	40 N
	Tear resistance (cd)	(EN 13937)	45 N
	Surface Resistivity after 2 hours in a climate room	ASTM D-257	10 ⁷ - 10 ⁸ Ohm ²

Roll make-up	Core diameter	76 mm
	Max. diameter	600 mm
	Standard length	ap. 300 mts
	Wrapping	Individual foil

Average values, subject to normal production tolerances.

