

# Quality: PC11C

Determination	Method	Result	
Polymer	PVC coated	Conductive PVC	
Surface resistivity	EN 1149-1	1	1.54 x 10 <sup>E3</sup>
		2	1.24 x 10 <sup>E3</sup>
		3	1.09 x 10 <sup>E3</sup>
Surface resistivity	EN 1149-3	Measurement	90% decay time t90 (s)
		1	<0.01
		2	<0.01
		3	<0.01
Weight	ISO 536	630gsm	
Thickness	EN 20534	170 µm	
Breaking strength	EN ISO 13934	MD 1500N / CD 1500N	
Tearing strength	ISO 9073	MD 220N / CD 180N	
Elongation at break	EN ISO 13934	20%	

[www.tytpacksystem.com](http://www.tytpacksystem.com)