

DUPONT™ TYVEK® 1082D

PRODUCT PROPERTIES—METRIC UNITS

Product Features:
Antistatic Treatment
Corona Treated

Specification Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1082D
Basis Weight	DIN EN ISO 536 (96) ¹	g/m ²	105.0 [101.0–109.0]
Delamination	ASTM 2724-07 ²	N	1.7 [1.2–2.2]

Notes: All specification properties are typical values based on mill roll averages, with samples taken uniformly across the sheet.

1. Modified for size: 100 cm²
2. Modified for: result interpretation – length of delamination = 116 mm, width 25.4 mm, speed = 127 mm/min and clamp distance = 60 mm

Miscellaneous Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1082D
Thickness	DIN EN ISO 534 (05) ³	µm	275
Opacity	ISO 2471 (98) ⁴	%	> 97
Tensile Strength, MD	DIN EN ISO 1924-2 (08) ⁵	N	280
Tensile Strength, CD	DIN EN ISO 1924-2 (08) ⁵	N	315
Elmendorf Tear, MD	DIN EN 21974 (94)	N	8.0
Elmendorf Tear, CD	DIN EN 21974 (94)	N	7.4

Notes: Miscellaneous properties are typical values based on mill roll averages, unless otherwise noted but are not warranted in any way, expressed or implied. Miscellaneous properties are not controlled in the process and are subject to normal process drift.

MD = machine direction; CD = cross direction.

3. Surface 2 cm², pressure 50 kPa
4. Modified for: backing standards, measuring area, and illumination = wide area.
5. Modified for: speed = 100 mm/min, width = 25.4 mm and gauge length = 127 mm

For more information about DuPont™ Tyvek®, call us today at 1.800.44.TYVEK

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark, or technical information of DuPont or others covering any material or its use.

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and Tyvek® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. K-29580 (3/17)

DUPONT™ TYVEK® 1082D

PRODUCT PROPERTIES—ENGLISH UNITS

Product Features:
Antistatic Treatment
Corona Treated

Specification Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1082D
Basis Weight	DIN EN ISO 536 (96) ¹	oz/yd ²	3.10 [2.98–3.22]
Delamination	ASTM 2724-07 ²	lb _f	0.382 [0.267–0.495]

Notes: All specification properties are typical values based on mill roll averages, with samples taken uniformly across the sheet.

1. Modified for size: 100 cm²
2. Modified for: result interpretation – length of delamination = 116 mm, width 25.4 mm, speed = 127 mm/min and clamp distance = 60 mm

Miscellaneous Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1082D
Thickness	DIN EN ISO 534 (05) ³	mils	10.8
Opacity	ISO 2471 (98) ⁴	%	> 97
Tensile Strength, MD	DIN EN ISO 1924-2 (08) ⁵	lb _f	62.95
Tensile Strength, CD	DIN EN ISO 1924-2 (08) ⁵	lb _f	70.81
Elmendorf Tear, MD	DIN EN 21974 (94)	lb _f	1.80
Elmendorf Tear, CD	DIN EN 21974 (94)	lb _f	1.66

Notes: Miscellaneous properties are typical values based on mill roll averages, unless otherwise noted but are not warranted in any way, expressed or implied. Miscellaneous properties are not controlled in the process and are subject to normal process drift.

3. Surface 2 cm², pressure 50 kPa
4. Modified for: backing standards, measuring area, and illumination = wide area.
5. Modified for: speed = 100 mm/min, width = 25.4 mm and gauge length = 127 mm

MD = machine direction; CD = cross direction.

For more information about DuPont™ Tyvek®, call us today at 1.800.44.TYVEK

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark, or technical information of DuPont or others covering any material or its use.

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and Tyvek® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. K-29580 (3/17)